



DEFOAMER AG230

Defoamer AG230 is a specialty defoamer for use in conjunction with polycarboxylate concrete admixtures, as well as other industrial applications. AG230 is based on fatty alcohol EO/PO copolymer.

USAGE

In polycarboxylate formulations, the recommended dosage rate is 0.5-1.0% by weight of the polycarboxylate water reducer. Dosage should be adjusted by concrete air content before use.

PRODUCT SPECIFICATIONS

Parameters (units)	Specifications
Color (Pt-Co)	≤50
Cloud point (°C, 1% aqueous solution)	58~
pH (1% aqueous solution)	5.0-7.0
Viscosity (38°C, mPa.s)	135-175
H ₂ O (%)	≤ 0.3
Specific gravity (20°C)	1.05~



**LIMITED WARRANTY INFORMATION.
PLEASE READ CAREFULLY.**

Chemport Pty Ltd provides the information contained in this document in good faith based on the best knowledge available at the time of publication. While we believe the information to be accurate and reliable, it is intended for general guidance only and is provided without warranty of any kind, express or implied.

Users are solely responsible for determining the suitability of this product for their specific application and for ensuring compliance with all relevant regulations, industry standards, and intellectual property rights. The product must not be used in violation of any law, statute, or third-party rights.

Chemport Pty Ltd shall not be liable for any direct, indirect, or consequential loss or damage arising from the use of this product or reliance on the information provided in this document. Users should refer to the current Safety Data Sheet (SDS) and perform their own evaluations, including any necessary testing, to confirm the product's suitability for use in their particular conditions.

This document is subject to revision without notice as new data becomes available.

TECHNICAL SUPPORT
+61294103317
info@chemport.com.au

Level 9 Tower A
821 Pacific Highway
Chatswood NSW 2067
Australia

chemport.com.au

PACKAGING

200kg Drums and 1000kg totes

STORAGE & SHELF LIFE

Product should be stored in a dry place away from direct sunlight in sealed, original packaging.

SAFETY & HANDLING

Please consult the Material Safety Data Sheet for additional information on safety, handling and storage before using this product.